

INTERNATIONAL UNION OF PURE
AND APPLIED CHEMISTRY

MACROMOLECULAR DIVISION

COMMISSION ON MACROMOLECULAR NOMENCLATURE*

**STEREOCHEMICAL DEFINITIONS AND
NOTATIONS RELATING TO POLYMERS**

(Recommendations 1980)

Prepared for publication by

A. D. JENKINS

University of Sussex, Falmer, Brighton, UK

*Membership of the Commission for 1979-81 is as follows:

Chairman: A. D. JENKINS (UK); *Secretary:* N. M. BIKALES (USA); *Titular Members:* G. ALLEGRA (Italy); P. KRATOCHVÍL (Czechoslovakia); I. MITA (Japan); I. M. PAPISSOV (USSR); W. RING (FRG); P. SIGWALT (France); *Associate Members:* L. G. DONARUMA (USA); R. B. FOX (USA); K. L. LOENING (USA); R. H. MARCHESSAULT (Canada); S. PENCZEK (Poland); N. A. PLATÉ (USSR); U. W. SUTER (Switzerland); T. TSURUTA (Japan); R. E. WETTON (UK); *National Representatives:* E. M. VALLES ARAMBURU (Argentina); E. B. MANO (Brazil); H. YADONG (China).

Past Members/Other Active Contributors:

P. CORRADINI (Italy); L. C. CROSS (UK); J. F. KENNEDY (UK).

STEREOCHEMICAL DEFINITIONS AND NOTATIONS RELATING TO POLYMERS

IUPAC COMMISSION ON MACROMOLECULAR NOMENCLATURE

CONTENTS

	Page
PREAMBLE	735
1. BASIC DEFINITIONS	736
Definition	
Number	
1 Configurational unit	736
2 Configurational base unit	736
3 Configurational repeating unit	736
4 Stereorepeating unit	737
Note on enantiomeric and diastereoisomeric units	737
5 Tactic polymer	738
6 Tacticity	738
7 Isotactic polymer	738
8 Syndiotactic polymer	738
9 Stereoregular polymer	738
10 Atactic polymer	738
Note on atactic polymers	739
11 Stereospecific polymerisation	740
12 Ditactic polymer	740
13 Tritactic polymer	740
14 Diisotactic polymer	741
15 Disyndiotactic polymer	741
16 Cistactic polymer	741
17 Transtactic polymer	741
18 Block	742
19 Tactic block	742
20 Atactic block	742
21 Stereoblock	742
22 Tactic block polymer	742
23 Stereoblock polymer	742
2. SEQUENCES	743
2.1 Constitutional and configurational sequences	743
24 Constitutional sequence	743
25 Constitutional homosequence	743
26 Configurational sequence	743
27 Stereosequence	743
28 Configurational homosequence	744
29 Stereohomosequence	744


	Page	
2.2	Description of relative configurations	744
	Erythro and threo structures	744
	Meso and racemo structures	745
	Stereosequences: diads; triads; tetrads; <i>etc.</i>	747
3.	CONFORMATIONS	747
3.1	Designation of conformation of polymer molecules	747
	Bond lengths	747
	Bond angles	747
	Torsion angles	747
3.2	Specific terminology for crystalline polymers	749
	Helices	749
	Helix sense	749
	Isomorphous and enantiomorphous structures	749
	Isoclinal and anticlinal structures	749
	Line repetition groups and symmetry elements	750
	Chain symmetry of some crystalline polymers	751
4.	SUPPLEMENTARY DEFINITIONS	751
	Degrees of tacticity	751
	Degree of crystallinity	751
	Lateral order	752
	Longitudinal order	752
5.	REFERENCES	752

PREAMBLE

A report entitled 'Nomenclature Dealing with Steric Regularity in High Polymers' was issued in 1962 by a sub-committee of the Commission on Macromolecules of the IUPAC (1). Since then, the development of increasingly sophisticated techniques for structure-determination has greatly enlarged the field of polymer stereochemistry and this, in turn, has revealed the need for a detailed knowledge of molecular conformations in order to correlate chemical structure with physical properties. The nomenclature relating to the constitution and configuration of macromolecules has been refined, using structure-based concepts, in documents of this Commission (2,3), while an IUPAC paper (4) on the stereochemistry of organic molecules and an IUPAC-IUB document (5) on abbreviations and symbols to be used for the description of the conformations of polypeptide chains have appeared as definitive publications. The present statement is intended to bring up to date the nomenclature of features corresponding to stereoregularity in polymers; it employs the definitions prescribed in (2) and takes into account all the previously-elaborated material cited above; it also introduces new concepts dealing with the microstructure of polymer chains, and it proposes a set of definitions and notations for the description of the conformations of polymer molecules. Consistency with documents (4) and (5) has been maintained as far as is possible.

Throughout this document, stereochemical formulae for polymer chains are shown as Fischer projections rotated through 90° , i.e. displayed horizontally rather than vertically, [at variance with (1)] or as hypothetical extended zigzag chains; the latter occasionally give a clearer indication of the three-dimensional arrangement. It is preferred that the hypothetical extended zigzag chains be consistently drawn with the backbone bond on the extreme left of the formula presented rising from left to right and with the interrupted line, on any given backbone carbon atom, drawn to the left of the full line.


The use of rotated Fischer projections corresponds to the common practice of using horizontal lines to denote polymer backbone bonds, but it is most important to note that this does not give an immediately visual impression of the zigzag chain. In the projections as used in this document, at each individual backbone carbon atom the horizontal lines represent bonds directed below the plane of the paper from the carbon atom while the vertical lines project above the plane of the paper from the carbon atom. Thus, the rotated Fischer projection



Unless otherwise stated, the drawings of configurational base units, configurational repeating units, stereorepeating units, *etc.*, provide information regarding relative configurations.

In a polymer molecule, the two portions of the main chain attached to any constitutional unit are, in general, non-identical; consequently, a backbone carbon atom that also bears two different side-groups is considered to be a chiral centre.

The absence from a formula of any one of the horizontal or vertical lines at a chiral or prochiral carbon atom (as in examples on pages 739 and 743), or of *cis* or *trans* designations at double bonds, indicates that the configuration of that stereoisomeric centre is not known. Also, as in our previous document (2), the convention of orienting polymer structures (and the corresponding constitutional and configurational units) from left to right is used. Thus, the two bracketted constitutional units in



are regarded as different, even though the repetition of either one of them would give the same regular polymer. Some of the definitions presented also appear in a previous paper of this Commission (2), but they are repeated here (with minor grammatical improvement) in order to provide a complete set of stereochemical definitions in a single document.


In order to present clear concepts it is necessary that idealised definitions be adopted but it is recognised that the realities of polymer science must be faced. Deviations from ideality arise with polymers at both molecular and bulk levels in ways that have no parallel with the ordinary small molecules of organic or inorganic chemistry. Although such deviations are not explicitly taken into account in the definitions below, the nomenclature recommended can usefully be applied to the predominant structural features of real polymer molecules, if necessary with self-explanatory, if imprecise, qualifications such as 'almost completely isotactic' or 'highly syndiotactic'. Although such expressions lack the rigour beloved of the purist, every experienced polymer scientist knows that communication in this discipline is impossible without them.

1. BASIC DEFINITIONS


- Configurational unit A constitutional unit having one or more sites of defined stereoisomerism.
- Configurational base unit A constitutional repeating unit, the configuration of which is defined at one or more sites of stereoisomerism in the main chain of a polymer molecule.

In a regular polymer, a configurational base unit corresponds to the constitutional repeating unit.


- Configurational repeating unit The smallest set of one, two or more successive configurational base units that prescribes configurational repetition at one or more sites of stereoisomerism in the main chain of a polymer molecule.



are not enantiomeric, but diastereoisomeric. The simplest possible stereorepeating units in a stereoregular poly(propylene) are



and the corresponding stereoregular polymers are



[4]

[5]

[6]

(an isotactic polymer, see Definition 7)

(a syndiotactic polymer, see Definition 8.)

(a hypothetical heterotactic polymer, see Section 2.2)

5. Tactic polymer

A regular polymer, the molecules of which can be described in terms of only one species of configurational repeating unit in a single sequential arrangement.

6. Tacticity

The orderliness of the succession of configurational repeating units in the main chain of a polymer molecule. (For the definition of degree of tacticity, see Section 4.)

7. Isotactic polymer

A regular polymer, the molecules of which can be described in terms of only one species of configurational base unit (having chiral or prochiral atoms in the main chain) in a single sequential arrangement.

Note In an isotactic polymer, the configurational repeating unit is identical with the configurational base unit.

8. Syndiotactic polymer

A regular polymer, the molecules of which can be described in terms of alternation of configurational base units that are enantiomeric.

Note In a syndiotactic polymer, the configurational repeating unit consists of two configurational base units that are enantiomeric.

9. Stereoregular polymer


A regular polymer, the molecules of which can be described in terms of only one species of stereorepeating unit in a single sequential arrangement.

10. Atactic polymer

A regular polymer, the molecules of which have equal numbers of the possible configurational base units in a random sequence distribution.

Examples


For the polymer $\left[\text{CH}(\text{COOR})\text{CH}(\text{CH}_3) \right]_n$, if only the ester-bearing main-chain site in each constitutional repeating unit has defined stereochemistry, the configurational repeating unit is [7] and the corresponding isotactic polymer is [8].




[7]

[8]

In the corresponding syndiotactic case, the configurational repeating unit is [9] and the syndiotactic polymer is [10]:





As the definition of a stereoregular polymer (see Definitions 4 and 9) requires that the configuration be defined at all sites of stereoisomerism, structures [8] and [10] do not represent stereoregular polymers. The same is true of [11] and [12], which differ from [8] and [10] in that the sites of specified and unspecified configuration have been interchanged.





Examples [4], [5], [6], [8], [10], [11], and [12] are tactic polymers. A stereoregular polymer is always a tactic polymer, but a tactic polymer is not always stereoregular because a tactic polymer need not have all sites of stereoisomerism defined.

Further examples of tactic polymers are:



isotactic poly(oxypropylene)



isotactic poly(ethylidene)



syndiotactic poly(ethylidene)



Note Structure-based names of tactic polymers are formed before the application of adjectives designating tacticity; thus, 'syndiotactic poly(ethylidene)' is preferred to 'syndiotactic poly(dimethylethylene)' because a shorter repeating unit is identified, in conformity with the rules in reference (3).

Note on atactic polymers

As the definition above indicates, a regular polymer, the configurational base units of which contain one site of stereoisomerism only, is atactic if it has equal numbers of the possible types of configurational base units arranged in a random distribution. If the constitutional repeating unit contains more than one site of stereoisomerism, the polymer may be atactic with respect to only one type of site if there are equal numbers of the possible configurations of that site arranged in a random distribution.

14. Diisotactic polymer

An isotactic polymer that contains two chiral or prochiral atoms with defined stereochemistry in the main chain of the configurational base unit.

15. Disyndiotactic polymer


A syndiotactic polymer that contains two chiral or prochiral atoms with defined stereochemistry in the main chain of the configurational base unit.

Examples


Diisotactic



Disyndiotactic (see Note a)



A polymer with the repeating unit



is ditactic and may be described as syndiotactic (see Definition 8), but it is not disyndiotactic.

The relative configuration of adjacent, constitutionally non-equivalent, carbon atoms can be specified as 'erythro' or 'threo', as appropriate, by adding the required prefix to the terms 'diisotactic' and 'disyndiotactic', as necessary (see Section 2.2).

16. Cistactic polymer


A tactic polymer in which the main-chain double bonds of the configurational base units are entirely in the *cis* arrangement.

17. Transtactic polymer

A tactic polymer in which the main-chain double bonds of the configurational base units are entirely in the *trans* arrangement.

Terms referring to the tacticity of polymers (tactic, ditactic, tritactic, isotactic, cistactic, *etc.*) can also be applied with similar significance to chains, sequences, blocks, *etc.*



Note Terms defining stereochemical arrangements are to be italicised only when they form part of the name of a polymer; the use of such terms as adjectives, even when immediately preceding names, does not require italics. This practice is illustrated in the examples below.




does not represent a different disyndiotactic polymer.

ExamplesIsotactic poly(3-methyl-*trans*-1-butenylene)

transisotactic poly(3-methyl-1-butenylene) (see Note a)

diisotactic poly[*threo*-3-methoxycarbonyl-4-methyl-*trans*-1-butenylene]trans*threo*diisotactic poly[3-methoxycarbonyl-4-methyl-1-butenylene] (see Note a)

and/or

18. Block

A portion of a polymer molecule, comprising many constitutional units, that has at least one constitutional or configurational feature which is not present in the adjacent portions.

19. Tactic block

A regular block that can be described by only one species of configurational repeating unit in a single sequential arrangement.

20. Atactic block

A regular block that has equal numbers of the possible configurational base units in a random sequence distribution.

21. Stereoblock

A regular block that can be described by one species of stereorepeating unit in a single sequential arrangement.

22. Tactic block polymer


A polymer, the molecules of which consist of tactic blocks connected linearly.

23. Stereoblock polymer

A polymer, the molecules of which consist of stereoblocks connected linearly.


Examples

tactic block polymer




where A and B are, for example,

Note a. These are both structure-based names; either may be used.



In this case the blocks are stereoblocks but the block polymer is not a block copolymer because all the units derive from a single monomer.

In the following example of a regular poly(propylene) chain, the stereoblocks are denoted by \square . Here, the sequence of identical relative configurations of adjacent units that characterises the stereoblock is terminated at each end of the block. Note that \square represents a configurational sequence, which may or may not be identical with a stereoblock (see definitions 21 and 26).



The configurational sequence and stereosequence coincide in this particular case because there is only one site of stereoisomerism in each constitutional repeating unit (compare definitions 26 and 27).

2. SEQUENCES


2.1 Constitutional and configurational sequences

The description of polymer structure revealed by studies of physical properties focuses attention on the distribution of local arrangements present in the molecules, and terms useful in this context are defined below. (The terms defined here in relation to complete polymer molecules can also be applied to sequences and to blocks, as in reference (2), Definition 3.14).

24. Constitutional sequence

A defined portion of a polymer molecule comprising constitutional units of one or more species.



Examples



25. Constitutional homosequence

A constitutional sequence which contains constitutional units of only one species and in one sequential arrangement.

Examples



In these two cases, the constitutional unit $-\text{CH}(\text{CH}_3)-\text{CH}_2-$ can be called the constitutional repeating unit of the homosequence.

26. Configurational sequence

A constitutional sequence in which the relative or absolute configuration is defined at one or more sites of stereoisomerism in each constitutional unit in the main chain of a polymer molecule. (See example following Definition 23.)

27. Stereosequence

A configurational sequence in which the relative or absolute configuration is defined at all sites of stereoisomerism in the main chain of a polymer molecule.

29. Configurational homosequence

A constitutional homosequence in which the relative or absolute configuration is defined at one or more sites of stereoisomerism in each constitutional unit in the main chain of a polymer molecule.

29. Stereohomosequence

A configurational homosequence in which the relative or absolute configuration is defined at all sites of stereoisomerism in the main chain of a polymer molecule.


2.2 Description of relative configurations

Erythro and threo structures


The relative configuration at two contiguous carbon atoms in the main chain bearing, respectively, substituents a and b ($a \neq b$), is designated by the prefix 'erythro' or 'threo', as appropriate, by analogy with the terminology for carbohydrate systems (see Note a) in which the substituents are -OH.

Examples

erythro






threo




Similar systems in which a higher level of substitution exists may be treated analogously if the erythro or threo designation is employed to denote the relative placements of those two substituents, one for each backbone carbon atom, which rank highest according to the Sequence Rule. Thus, the following hypothetical examples would be designated as indicated:

Examples



erythro



threo



Note a. See Rule 4.11 of reference (4).




This novel extension of the erythro/threo terminology, especially its conjunction with the Sequence Rule, is specifically proposed solely to cope with the problems incurred in describing the steric structures of macromolecules.

Meso and racemo structures


Relative configurations of consecutive, but not necessarily contiguous, constitutionally equivalent carbon atoms that have a symmetrically-constituted connecting group (if any) are designated as 'meso' or 'racemo', as appropriate.


Examples

meso




racemo




(The symbol  represents a symmetrically-constituted connecting group, such as -CH₂-, -CH₂-CH₂-, or -CR₂-CH₂-CR₂-.)

Note The structures




both have the meso relative configuration but the boldly-printed carbon atoms in each of the formulae below cannot be considered as in a meso arrangement because the connecting group lacks the necessary symmetry.




The term 'racemo' is introduced here as the logical prefix for the designation of an arrangement that is analogous to racemic, in the sense defined above. It is unfortunate that the meaning of the term 'racemic' current in organic chemistry is not directly applicable to polymers, but the use of the prefix 'racemo' proposed here should not cause confusion because of the special context. To achieve a full configurational description, it may be necessary to preface the name of a polymer with a compound adjective that combines a term such as 'erythro', 'threo', 'meso', or 'racemo' with a term such as 'diisotactic' or 'disyndiotactic'.

Examples


erythrodiisotactic polymer



threodiisotactic polymer




disyndiotactic polymer (see Note a)




Polymers with chiral centres arising from rings linking adjacent main-chain carbon atoms can be included in this nomenclature:

erythrodiisotactic polymer




threodiisotactic polymer




In the last two cases, the chiralities of the asymmetric centres should be designated *R*- or *S*-, if known.

erythrodisyndiotactic polymer




threodisyndiotactic polymer




Note a. This polymer cannot be expressed as erythrodisyndiotactic nor as threodisyndiotactic. Instead:

erythrodisyndiotactic




threodisyndiotactic




If the rings are symmetrical:

mesodiisotactic




racemodiisotactic



Stereosequences

Stereosequences terminating in tetrahedral stereoisomeric centres at both ends, and which comprise two, three, four, five, *etc.* consecutive centres of that type, may be called diads, triads, tetrads, pentads, *etc.*, respectively.

Typical diads are:



When it is necessary to specify the internal stereochemistry of the group, a prefix is required. In vinyl polymers there are meso (*m*) and racemic (*r*) diads and *mm*, *mr*, *rr* triads. The latter may be called isotactic, heterotactic, and syndiotactic triads, respectively. Stereoregular vinyl polymers can be defined in terms of the regular sequences of diads; thus an isotactic vinyl polymer consists entirely of *m* diads, *i.e.*, it corresponds to the following succession of relative configuration *-m m m m m m-*, whereas a syndiotactic vinyl polymer consists entirely of *r* diads, corresponding to the sequence *-r r r r r r-*. Similarly, a vinyl polymer consisting entirely of *mr* (*=rm*) triads is called a heterotactic polymer.

3. CONFORMATIONS


3.1 Designation of conformation of polymer molecules

Bond lengths

If a specific A-B bond is denoted as A_i-B_j , the bond length is written $b(A_i, B_j)$. Abbreviated notations, such as b_i , may be used if this meaning is clarified by a diagram.

Bond angles


The bond angle formed by three consecutive atoms



is written $\tau(A_i, B_j, C_k)$ which may be abbreviated, if there is no ambiguity, to $\tau(B_j)$, τ_j^B , $\tau_B(j)$ or τ_j .

Torsion angles

If a system of four consecutive atoms



is projected onto a plane normal to bond B-C, the angle between the projection of A-B and the projection of C-D is described as the torsion angle of A and D about bond B-C; this angle may also be described as the angle between the plane containing A, B and C and the plane containing B, C, and D. The torsion angle is written in full as $\theta(A_i, B_j, C_k, D_l)$, which may be abbreviated, if there is no ambiguity, to $\theta(B_j, C_k)$, $\theta(B_j)$, or θ_j^B , *etc.* In the eclipsed conformation in which the projections of A-B and C-D coincide, θ is given the value 0° (synperiplanar conformation). A torsion angle is considered positive ($+\theta$) or negative ($-\theta$) depending on whether, when the system is viewed along the central bond in the direction B—C (or C—B), the bond to the front atom A (or D) requires the smaller angle of rotation to the right or to the left, respectively, in order that it

may eclipse the bond to the rear atom D (or A); note that it is immaterial whether the system be viewed from one end or the other. According to this definition, a sequence of consecutive positive torsion angles generates a right-handed helix (Helix Sense, p. 749).

It is to be noted that:

- (i) torsion angles are measured in the range $-180^\circ < \theta < +180^\circ$ rather than from 0° to 360° , so that the relationship between enantiomeric configurations or conformations can be readily appreciated;
- (ii) any Greek letter from the end of the alphabet, except τ , can be used to denote torsion angles; θ or ω is recommended;
- (iii) abbreviated notations are preferably restricted to bond lengths, bond angles, and torsion angles related to main-chain atoms.

Conformations referring to torsion angles $\theta(A, B, C, D)$, where A, B, C, D are main-chain atoms, can be described as: *cis* or *synperiplanar* (C); *gauche* or *synclinal* (G); *anticlinal* (A); and *trans* or *antiperiplanar* (T), corresponding to torsion angles within $\pm 30^\circ$ of, respectively, 0° , $\pm 60^\circ$, $\pm 120^\circ$ and $\pm 180^\circ$. The letters shown in parentheses (upper case C, G, A, T) are the recommended abbreviations (see Note a).


The symbols G^+ , G^- (or A^+ , A^- , for example) refer to torsion angles of similar type but opposite known sign, *i.e.* $\sim +60^\circ$, $\sim -60^\circ$ (or $\sim +120^\circ$, $\sim -120^\circ$). The notation G , \bar{G} ; A , \bar{A} (and T , \bar{T} ; C , \bar{C} whenever the torsion angles are not exactly equal to 180° and 0° , respectively) is reserved for the designation of enantiomorph conformations, *i.e.* conformations of opposite but unspecified sign. Where necessary, a deviation from the proper value of the torsion angle can be indicated by the sign (\sim), as in the following examples: $G(\sim)$; $\bar{G}(\sim)$; $G^+(\sim)$; $G^-(\sim)$.

Examples


The chain conformation of isotactic poly(propylene) in the crystalline state is:



The chain conformation of syndiotactic poly(propylene) in the crystalline state is:




The chain conformation of a right-handed α -helix is:



The symbols (cis) and (trans) may be used to designate rigid dihedral angles such as those occurring with double bonds.


The chain conformation of crystalline poly(1,1-difluoroethylene), modification 2, is:




The chain conformation of crystalline poly(*trans*-1-methyl-1-butenylene) in the α form is:



The chain conformation of isotactic vinyl polymers in the crystalline state is:



A possible conformation of isotactic poly(propylene) in the melt can be described as:



Note a. Different authors variously use the upper and lower case letters in this context. The desire for uniformity necessitates an arbitrary choice between the alternatives, and the upper case has been selected in the belief that it conflicts less with other designations, for example, the use of *c* and *t* on pages 749 and 751.

3.2 Specific terminology for crystalline polymers

The crystallographic identity period parallel to the chain axis should preferably be designated c in descriptions of macromolecular crystallography.

In the description of helices, the following parameters and symbols should be employed:

n signifies the number of conformational repeating units per turn

(The conformational repeating unit in a crystalline polymer is the smallest unit of given conformation that is repeated through symmetry operations which comprise a translation. In most cases it corresponds to the configurational repeating unit.)

h signifies the unit height, *i.e.*, the translation along the helix axis per conformational repeating unit.

t signifies the unit twist, *i.e.*, the angle of rotation about the helix axis per conformational repeating unit.

Examples

If the number of conformational repeating units along the identity period c is M and the number of turns is N , then:

$$n = M/N, \quad h = c/M, \quad t = 2\pi N/M.$$

For isotactic poly(propylene), since $M = 3$, $N = 1$ and $c = 6.50 \text{ \AA}$

$$n = 3, \quad h = 2.17 \text{ \AA}, \quad t = 2\pi/3.$$

For poly(oxymethylene), since $M = 9$, $N = 5$ and $c = 17.39 \text{ \AA}$,

$$n = 1.8, \quad h = 1.93 \text{ \AA}, \quad t = 2\pi(5/9).$$

Helix sense

The right-handed sense of a helix traces out a clockwise rotation moving away from the observer; the left-handed sense of a helix traces out a counterclockwise rotation moving away from the observer, *e.g.* the ...TG⁺TG⁺TG⁺... helix of isotactic poly(propylene) is left-handed.

Isomorphous and enantiomorphous structures

In the crystalline state, polymer chains are generally parallel to one another but neighbouring chains of equivalent conformation may differ in chirality and/or orientation.

Chains of identical chirality and conformation are isomorphous. Chains of opposite chirality but equivalent conformation are enantiomorphous.


Examples

Two ...TG⁺TG⁺TG⁺... helices of isotactic poly(propylene) are isomorphous.

Isotactic poly(propylene) chains of the ...TG⁺TG⁺TG⁺... and ...G⁻TG⁻TG⁻T... types are mutually enantiomorphous.

Isoclined and anticlined structures

With regard to orientation, consider a repeating side group originating at atom A_1^i , the first atom of the side group being B_α^i . For certain chain symmetries (helical, for instance) the bond vectors $\vec{b}(A_1^i, B_\alpha^i)$ have the same components (positive or negative) $b.c/|c|$ along the c axis for every i .




Two equivalent (isomorphous or enantiomorphous) chains in the crystal lattice, having identical components of the bond vectors along c , both positive or both negative, are designated isoclined; two equivalent chains having bond vectors along c of the same magnitude but opposite sign are designated anticlined.


Examples

(i) Isotactic poly(3-methyl-*cis*-1-butenylene)

Isoclined isomorphous chains:
the two chains have parallel
axes and the same orientation
of the pendant methyl groups.




Anticlined isomorphous chains:
the two chains have parallel
axes and opposite orientation
of the pendant methyl groups.



(ii) Isotactic poly(propylene)

Anticlined enantiomorphous chains:
the conformation of A corresponds
to a $(TG^-)_n$ bond succession
(right-handed helix). The con-
formation of B corresponds to a
 $(G^+T)_n$ bond succession (left-
handed helix).



Line repetition groups and symmetry elements

To designate linear chain conformations in the crystalline state, the use of line repetition groups (6) is recommended.

First symbol

Ⓣ translation (Ⓣ bold type)

Ⓢ screw repetition (Ⓢ bold type)

[In this case of screw repetition, the number of conformational repeating residues per turn is included in parentheses, *i.e.*: $s(11/3)$ or $s(3.67 \pm 0.02)$.]

Second and further symbols. The symmetry elements required to define the line repetition group are suggested in reference (7). Possible symmetry elements are:

- i* centre of symmetry
- m* plane of symmetry perpendicular to the chain axis
- c* glide plane parallel to the chain axis
- d* plane of symmetry parallel to the chain axis
- 2 two-fold axis of symmetry perpendicular to the chain axis

The possible line repetition groups are listed below, with examples. (The structure-based name is given first, the process-based name second, in each case.)

TABLE Chain symmetry of some crystalline polymers

Line repetition group	Polymer
<i>t l</i>	poly(1-methyl- <i>trans</i> -1-butenylene) trans-1,4-polyisoprene
<i>s</i> (M/N) 1	isotactic poly(propylene) (M/N = 3/1) isotactic polypropylene (M/N = 3/1)
<i>s</i> (M/N) 2	syndiotactic poly(propylene) (M/N = 2/1) (helical modification) syndiotactic polypropylene (M/N = 2/1) (helical modification)
<i>t m</i>	poly[imino(1,7-dioxoheptamethylene)iminoheptamethylene] poly(heptamethylene pimelamide)
<i>t c</i>	poly(1,1-difluoroethylene) (modification 2) poly(1,1-difluoroethylene) (modification 2)
<i>t i</i>	diisotactic poly(1,2-dimethyltetramethylene) diisotactic alternating copolymer of ethylene and <i>cis</i> -2-butene
<i>s</i> (2/1) <i>m</i>	poly(1-pentenylene) poly(cyclopentene)
<i>s</i> (2/1) <i>d</i>	poly[imino(1,6-dioxohexamethylene)iminohexamethylene] poly(hexamethylene adipamide)
<i>t d m</i>	-
<i>t i d</i>	-
<i>t c m</i>	syndiotactic poly(1-vinylethylene) syndiotactic 1,2-poly(1,3-butadiene)
<i>s</i> (2/1) <i>d m</i>	poly(ethylene) polyethylene

4. SUPPLEMENTARY DEFINITIONS (see Note a)

Degrees of triad isotacticity, syndiotacticity, and heterotacticity

The fractions of triads in a regular vinyl polymer that are of the *mm*, *rr* and *mr* = *rm* types, respectively. In cases where triad analysis is not attainable, the diad isotacticity and diad syndiotacticity may be defined as the fractions of diads in a regular vinyl polymer that are of the *m* and *r* types, respectively.

Degrees of cistacticity and transtacticity

For a regular polymer containing double bonds in the main chain of the constitutional repeating units, these are the fractions of such double bonds that are in the *cis* and *trans* configurations, respectively.

Degree of crystallinity

This is defined as the fraction of the bulk polymer that consists of regions showing long-range three-dimensional order.

Note a. Tacticity in side-chains will be treated in a later document.

Lateral order

Order in the side-by-side packing of the molecules of a linear polymer.

Longitudinal order

Order in the atomic positions along the chains of a linear polymer.

5. REFERENCES

1. M.L. Huggins, G. Natta, V. Desreux and H. Mark (for IUPAC Commission on Macromolecules). Report on Nomenclature Dealing with Steric Regularity in High Polymers. *J. Polymer Sci.*, **56**, 153 (1962); *Pure Appl. Chem.*, **12**, 643 (1966).
2. IUPAC Commission on Macromolecular Nomenclature. Basic Definitions of Terms Relating to Polymers 1974. *Pure Appl. Chem.*, **40**, 477 (1974).
3. IUPAC Commission on Macromolecular Nomenclature. Nomenclature of Regular Single-Strand Organic Polymers (Rules Approved 1975). *Pure Appl. Chem.*, **48**, 373 (1976).
4. IUPAC Commission on Nomenclature of Organic Chemistry. Rules for the Nomenclature of Organic Chemistry. Section E: Stereochemistry (Recommendations 1974). *Pure Appl. Chem.*, **45**, 11 (1976).
5. IUPAC-IUB Commission on Biochemical Nomenclature. Abbreviations and Symbols for the Description of the Conformation of Polypeptide Chains (Rules Approved 1974). *Pure Appl. Chem.*, **40**, 293 (1974).
6. A. Klug, F.H.C. Crick and H.W. Wyckoff, *Acta Crystallogr.*, **11**, 199 (1958).
7. P. Corradini, Chain Conformation and Crystallinity: chapter in '*Stereochemistry of Macromolecules*', A. Ketley (Editor), Marcel Dekker, Inc., New York, Part III, 1-60 (1968).

Members of the Commission who have contributed actively to the preparation of the document are: Prof. G. Allegra, Dr. N.M. Bikales (Secretary 1979-), Prof. P. Corradini, Dr. L.C. Cross, Dr. R.B. Fox (Secretary 1968-1979), Prof. A.D. Jenkins (Chairman 1978-), Dr. J.F. Kennedy, Dr. P. Kratochvíl, Dr. K.L. Loening (Chairman 1968-78), Prof. I.M. Papissov, Prof. N.A. Platé, Prof. W. Ring, Prof. P. Sigwalt, Dr. U.W. Suter, Prof. T. Tsuruta, and Dr. R.E. Wetton.